

Ahlstrom-Munksjö Nano GT

Pulse-jet filtration media for gas turbines operating in dry environment with fine pollution.

Quality of air entering the turbine is a significant factor in the performance and lifetime of the gas turbine. Ahlstrom-Munksjö offers a complete range of filtration media developed for gas turbine applications, to meet specific market needs in various operational environments.

Ahlstrom-Munksjö **Nano GT** portfolio is based on our market reference CellTech filtration media, but coated with electrospun nanofibers on the upstream side.

With a self-supported structure, it combines leading performance in pleatability, with optimal mechanical filtration at low pressure drop and excellent self-cleaning behaviour, even with fine pollution.

Ahlstrom-Munksjö **Nano GT** delivers excellent protection of the gas turbine and long filtration life time in dry environments.

Benefits

- ✔ **Offers ePM1 80% (ISO16890) efficiency** – delivering excellent protection of gas turbine against fine dust.
- ✔ **Delivers lowest level of pressure drop** – minimizing energy consumption.
- ✔ **Optimal back-pulsing behaviour** – delivering longer time between service intervals.
- ✔ **High corrugation** – offering ideal performance for pleatability.


Ahlstrom-Munksjö Nano GT

NP70 is our main F9 (EN779:2012) **Nano GT** offer, reaching ePM1 80% at very low pressure drop, according to the new ISO16890 standard. It delivers up to 4 times more particulate removal of submicron particles (PM1) than a more traditional M5 material without significant increase of pressure drop, making it our recommended option for environments with fine pollution.

Additionally, the nano layer supports very good pulse-jet cleaning behavior, due to predominant surface filtration phenomena. Performance of both base material and nanolayer have been upgraded to guarantee better performance in humid conditions and consistent behaviour along the filter life time.

Nano GT grades are also available in a bromine-free Flame Retardant version, reaching F1 according to ISO53468.

Ideal pulse jet behavior according ISO 11057 (NP70)



Ahlstrom-Munksjö Nano GT – Key Grade Characteristics

Grades	Basis Weight	Efficiency Class		Thickness	Corrugation Depth	Air Permeability	MD Stiffness
	g/m ²	EN779-2012	ISO16890	µm	µm	L/m ² /s @200 Pa	g
NP 70	125	F9	ePM1 80%	320	450	185	4.7
NP 70 FR	130	F9	ePM1 80%	360	450	110	3.7

Contact Ahlstrom-Munksjö Sales: ✉ filtration@ahlstrom-munksjo.com

www.ahlstrom-munksjo.com



Disclaimer: The information supplied in this document is for guidance only and should not be construed as a warranty. All implied warranties are expressly disclaimed, including without limitation any warranty of merchantability of fitness for use. All users of the material are responsible for ensuring that it is suitable for their needs, environment and end use. All data is subject to change as Ahlstrom-Munksjö deems appropriate.